

Volara® Chemical Resistance

Volara Types

	<u>A</u>	<u>EO</u>	<u>M</u>	<u>AS</u>	<u>LM</u>	<u>TS</u>
Carbon Tetrachloride	+22	+25	+11	+13	+11	+8
Heptane	+14	+14	+10	+16	+13	+8
Methlethylketone	+6	-5	+1	-1	+3	+1
Toluene	+14	+40	+5	+15	+13	+16
Trichloroethylene	+35	+41	+12	+12	+12	+15
Xylene	+21	+47	+10	+20	+15	+28
Ethyl Alcohol	+5	+<1	+<1	+2	+<1	+1
Gasoline	+11	+21	-7	-<1	+4	+4
Ammonium Hydroxide	-<1	-2	+3	-11	+2	-2
Acetic Acid (10%)	-7	-8	-2	-3	-1	-20
Hydrochloric Acid (10%)	-7	-13	-12	-9	-1	-34
Nitric Acid (10%)	+5	+14	+2	-<1	+3	+7
Sulfuric Acid (10%)	-7	-5	-5	-5	+2	-20

ASTM D 543-84

7 Days Immersion @ 70° F

ALL DENSITIES

%Volume Change

-: Indicates Shrinkage

+: Indicates Expansion