## SEKISUI | VOLTEK

## Technical Data Volara® Type TS

## **PRODUCT DEFINITION**

Volara type TS is specially formulated for the industrial tape and gasket markets. This material is a polyblend of two resin types, combined to provide the conformability, compression strength and toughness required to meet the demands of the mounting and assembly tape industries.

Type TS makes an ideal foam tape substrate as the composition was engineered to improve adhesive anchorage. Type TS is not approved for medical or food contact applications.



#### PRODUCT CHARACTERISTICS

- Improved adhesive anchorage
- Premium industrial tape substrate
- Excellent chemical resistance
- Ideally suited for industrial applications

#### PRODUCT FORM

Produced in roll form up to 1500 lineal feet

- Density: 2pcf to 6pcf
- Thickness range: 0.031" to 0.375"
- Width range to 61"

#### PRODUCT COLORS

Standard colors are natural-white and black

• Custom colors are available on request

#### **APPLICATIONS**



### **Michigan Location**

Sekisui Voltek, LLC 17 Allen Avenue Coldwater, MI 49036 www.SekisuiVoltek.com Tel: (**833) 517-1627** Fax: (**517) 279-8562** 



## Fine-celled, Irradiation cross-linked, Polyolefin Foam

# Volara<sup>®</sup> TS

TYPICAL PROPERTIES OF <b>VOLARA TS</b>		
	3pcf	5pcf
Compression Strength / (ASTM D3575)		
(lb / sq-in) @ 25% compression	7	8
(lb / sq-in) @ 50% compression	16	19
Tensile Strength / (ASTM D3575)		
(lb / sq-in) Machine Direction	126	226
(lb / sq-in) Cross-Machine Direction	96	146
Tensile Elongation / (ASTM D3575)		
(%) Machine Direction	232	284
(%) Cross-Machine Direction	224	263
Tear Resistance / (ASTM D3575)		
(lb / in) Machine Direction	17	28
(lb / in) Cross-Machine Direction	20	35
Compression Set / (ASTM D3575)		
% Original Thickness	20	7
Shore Hardness / (ASTM D2240)		·
A Scale	8	15
OO Scale	52	60
Thermal Stability		
AVE MD%	-1.6	-1.2
AVE CD% Change	-0.7	-0.55
AVE TH%	NA	NA

#### NOTE:

This data represented on this technical data sheet should be used as a guideline for product selection. This data is not intended to represent, replace or be used as a proxy for a specific productsales specification. The physical properties are averages based on limited production runs and are subject to change as additional

February, 2016

